



Viton[®] fluoroelastomer

From DuPont Performance Elastomers

Viton[®] A-331C

Introduction

Viton[®] A-331C* is an incorporated cure “A-family” dipolymer designed for the injection and transfer molding of parts requiring improved demolding “hot tear” resistance. The moderate viscosity level of Viton[®] A-331C also allows for satisfactory compression molding of parts.

Features of Viton[®] A-331C are:

- Intermediate viscosity level (when compared with related “O-ring” polymers Viton[®] A-202C/Viton[®] A-402C)
- Fully precompounded
 - reduced curative level
 - incorporated process aid
- Improved processing
 - increased mold flow
 - better mold release with less mold fouling
 - improved demolding “hot tear”
- Good compression set resistance

Applications

- Injection, transfer and compression molding of:
 - O-rings, seals, and gaskets
 - Other profiles requiring improved demolding “hot tear”
- Extruded O-ring cord, hose, and other profiles

Use of Viton[®] A-331C

Table 1 compares compounds of Viton[®] A-331C, Viton[®] E-60, Viton[®] A-202C, and Viton[®] A-402C. Table 2 compares the effects of carbon black levels in Viton[®] A-331C, and Table 3 compares the use of mineral fillers in Viton[®] A-331C.

Product Description

Chemical Composition	Dipolymer of hexafluoropropylene, and vinylidene fluoride plus cure chemicals and process aid
Physical Form	Slab
Color	Off-white
Odor	None
Specific Gravity	1.82
Solubility	Low molecular weight esters and ketones
Storage Stability	Excellent
Mooney Viscosity (ML 1 + 10 at 121°C [250°F])	30

Safety and Handling

Before handling or processing Viton[®] A-331C, read and follow the recommendations in the DuPont Performance Elastomers technical bulletin “Handling Precautions for Viton[®] and Related Chemicals.”

Viton[®] A-331C should be handled like other types of Viton[®]. Keep off skin and wash well after handling. For the safe handling of other compounding ingredients, refer to the respective manufacturers’ literature.

*Viton[®] A-331C was formerly VTR-6676.

Table 1
The Performance of Viton® A-331C in Typical Compounds

	A Viton® A-331C	B Viton® E-60	C Viton® A-202C	D Viton® A-402C
Viton® A-331C	100	—	—	—
Viton® E-60	—	96	—	—
Viton® A-202C	—	—	100	—
Viton® A-402C	—	—	—	100
High-Activity MgO	3	3	3	3
Calcium Hydroxide	6	6	6	6
MT Black (N990)	30	30	30	30
VPA #3	—	1	—	—
Viton® Curative #20	—	1.5	—	—
Viton® Curative #30	—	2.5	—	—
Stock Properties				
Viscosity, ML 1 + 10 at 121°C [250°F]				
Units	65	73	54	77
Mooney Scorch, MS at 121°C [250°F]				
Minimum, in-lb	34	39	29	41
2-pt rise, min	25.8	16.6	>30	29.1
5-pt rise, min	>30	21.7	—	>30
ODR at 177°C [350°F], Microdie, 3° Arc, 15 min				
M _L , in-lb	16	18	12	20
t _{s2} , min	1.4	1.5	1.8	1.6
t _{c90} , min	3.0	4.8	3.0	3.1
M _{c90} , in-lb	77	79	111	119
M _H , in-lb	83	85	121	130
Rosand Capillary Rheometer at 100°C [212°F], 1.5 mm Die, L/D = 0/1				
<i>Piston Speeds</i>			<i>Pressure, MPa</i>	
	<i>Shear Rate</i>			
12.7 mm/min	113 s ⁻¹	6.9	7.6	7.2
50.8 mm/min	452 s ⁻¹	10.1	13.2	11.5
127 mm/min	1130 s ⁻¹	16.0	30.9	18.5
Vulcanizate Properties				
Slabs Cure: 10 min at 177°C [350°F]				
Post Cure: 24 hr at 232°C [450°F]				
Stress/Strain at 23°C [73°F]—Original, no post cure				
100% Modulus, MPa [psi]	3.1 [455]	3.3 [475]	4.4 [645]	4.8 [700]
Tensile Strength, MPa [psi]	9.7 [1410]	8.6 [1240]	9.1 [1320]	9.4 [1370]
Elongation at Break, %	351	304	243	225
Hardness, durometer A, points	71	74	76	78
Stress/Strain at 23°C [73°F]—Original, post cure				
100% Modulus, MPa [psi]	4.5 [655]	5.0 [720]	6.8 [980]	7.1 [1030]
Tensile Strength, MPa [psi]	13.5 [1955]	11.8 [1715]	14.0 [2030]	13.8 [2005]
Elongation at Break, %	237	216	190	181
Hardness, durometer A, points	77	75	80	77
Stress/Strain at 23°C [73°F]—After aging 70 hr at 200°C [392°F]				
100% Modulus, MPa [psi]	4.6 [670]	5.1 [740]	7.4 [1070]	7.3 [1060]
Tensile Strength, MPa [psi]	14.5 [2100]	11.9 [1730]	13.8 [1995]	13.8 [2000]
Elongation at Break, %	240	206	171	175
Hardness, durometer A, points	75	77	82	79
Stress/Strain at 23°C [73°F]—After aging 168 hr at 200°C [392°F]				
100% Modulus, MPa [psi]	4.5 [655]	5.4 [780]	7.0 [1010]	7.2 [1050]
Tensile Strength, MPa [psi]	15.0 [2180]	12.2 [1765]	13.5 [1960]	13.0 [1880]
Elongation at Break, %	263	209	181	170
Hardness, durometer A, points	72	75	79	78
Stress/Strain at 23°C [73°F]—After aging 70 hr at 232°C [450°F]				
100% Modulus, MPa [psi]	4.9 [710]	5.2 [750]	7.5 [1085]	7.7 [1115]
Tensile Strength, MPa [psi]	14.1 [2040]	11.8 [1710]	13.9 [2015]	14.2 [2060]
Elongation at Break, %	230	202	169	168
Hardness, durometer A, points	76	78	81	80
Compression Set, Method B, O-rings, %				
70 hr at 23°C [73°F]	18	20	9	9
70 hr at 200°C [392°F]	21	29	16	14
168 hr at 200°C [392°F]	29	37	23	19
70 hr at 232°C [450°F]	40	51	39	34

Table 2
The Effect of Carbon Black Level in Viton® A-331C

	E 60 phr	F 45 phr	G 30 phr	H 15 phr	I 5 phr	J 2 phr
Viton® A-331C	100	100	100	100	100	100
High-Activity MgO	3	3	3	3	3	3
Calcium Hydroxide	6	6	6	6	6	3
MT Black (N990)	60	45	30	15	5	2
Stock Properties						
Viscosity, ML 1 + 10 at 121°C [250°F]						
Units	97	80	65	51	45	39
Mooney Scorch, MS at 121°C [250°F]						
Minimum, in-lb	54	43	34	27	23	20
2-pt rise, min	20.1	21.7	25.8	28	>30	>30
5-pt rise, min	29.6	>30	>30	>30	—	—
ODR at 177°C [350°F], Microdie, 3° Arc, 15 min						
M _L , in-lb	21	19	16	15	13	12
t _{s2} , min	1.3	1.4	1.4	1.5	1.8	2.2
t _{c90} , min	3.9	3.5	3.0	3.0	3.1	3.8
M _{c90} , in-lb	90	84	77	70	63	59
M _H , in-lb	97	91	83	76	68	64
Vulcanizate Properties						
Slabs Cure: E, F, G, H—10 min at 177°C [350°F]; I, J—30 min at 166°C [330°F]; blisters appeared at 177°C [350°F]						
Post Cure: 24 hr at 232°C [450°F]						
Stress/Strain at 23°C [73°F]—Original, no post cure						
100% Modulus, MPa [psi]	6.1 [890]	4.8 [700]	3.1 [455]	2.0 [295]	1.3 [195]	1.2 [170]
Tensile Strength, MPa [psi]	9.9 [1440]	10.1 [1460]	9.7 [1410]	8.1 [1170]	7.7 [1110]	5.8 [845]
Elongation at Break, %	273	336	351	314	350	315
Hardness, durometer A, points	88	83	71	63	58	54
Stress/Strain at 23°C [73°F]—Original, post cure						
100% Modulus, MPa [psi]	9.9 [1440]	6.9 [1005]	4.5 [655]	2.3 [330]	1.5 [220]	1.2 [170]
Tensile Strength, MPa [psi]	15.1 [2185]	14.4 [2095]	13.5 [1955]	12.6 [1825]	10.0 [1445]	5.8 [840]
Elongation at Break, %	165	206	237	306	315	288
Hardness, durometer A, points	88	83	77	67	59	53
Stress/Strain at 23°C [73°F]—After aging 70 hr at 200°C [392°F]						
100% Modulus, MPa [psi]	10.2 [1475]	8.0 [1155]	4.6 [670]	2.3 [340]	1.5 [215]	1.2 [180]
Tensile Strength, MPa [psi]	14.5 [2105]	14.8 [2140]	14.5 [2100]	13.2 [1920]	10.3 [1500]	7.7 [1120]
Elongation at Break, %	147	183	240	288	304	301
Hardness, durometer A, points	90	84	75	63	58	53
Stress/Strain at 23°C [73°F]—After aging 168 hr at 200°C [392°F]						
100% Modulus, MPa [psi]	10.4 [1515]	7.8 [1135]	4.5 [655]	2.5 [365]	1.6 [230]	1.3 [185]
Tensile Strength, MPa [psi]	15.1 [2185]	15.4 [2235]	15.0 [2180]	12.9 [1875]	10.2 [1480]	6.2 [895]
Elongation at Break, %	153	201	263	292	308	279
Hardness, durometer A, points	85	80	72	61	53	51
Stress/Strain at 23°C [73°F]—After aging 70 hr at 232°C [450°F]						
100% Modulus, MPa [psi]	10.5 [1525]	8.0 [1160]	4.9 [710]	2.3 [340]	1.5 [215]	1.2 [170]
Tensile Strength, MPa [psi]	15.0 [2180]	14.2 [2055]	14.1 [2040]	12.2 [1775]	10.8 [1560]	6.7 [975]
Elongation at Break, %	148	171	230	268	308	291
Hardness, durometer A, points	91	84	76	64	56	53
Compression Set, Method B, O-rings, %						
70 hr at 23°C [73°F]	23	20	18	14	13	13
70 hr at 200°C [392°F]	29	23	21	17	21	15
168 hr at 200°C [392°F]	37	30	29	24	22	18
70 hr at 232°C [450°F]	47	43	40	37	35	31

Table 3
The Effect of Mineral Fillers in Viton® A-331C

	K MT Black	L Albaglos®	M Nyad® 400	N Celite® 350	O Blanc Fixe	P Ti-Pure® R960
Viton® A-331C	100	100	100	100	100	100
High-Activity MgO	3	3	3	3	3	3
Calcium Hydroxide	6	6	6	6	6	3
MT Black (N990)	30	—	—	—	—	—
Albaglos®	—	30	—	—	—	—
Nyad® 400	—	—	30	—	—	—
Celite® 350	—	—	—	30	—	—
Blanc Fixe	—	—	—	—	30	—
Ti-Pure® R960	—	—	—	—	—	30
Stock Properties						
Viscosity, ML 1 + 10 at 121°C [250°F]						
Units	65	65	60	84	56	58
Mooney Scorch, MS at 121°C [250°F]						
Minimum, in-lb	34	35	32	46	31	31
2-pt rise, min	25.8	17.1	23.7	19.6	22.6	24.2
5-pt rise, min	>30	20.6	29.0	23.6	27.1	29.4
ODR at 177°C [350°F], Microdie, 3° Arc, 15 min						
M _L , in-lb	16	20	18	21	17	16
t _{s2} , min	1.4	1.3	1.4	1.4	1.5	1.8
t _{c90} , min	3.0	2.9	2.5	3.0	2.9	4.2
M _{c90} , in-lb	77	77	75	75	71	59
M _H , in-lb	83	83	81	81	77	64
Vulcanizate Properties						
Slabs Cure: 10 min at 177°C [350°F]						
Post Cure: 24 hr at 232°C [450°F]						
Stress/Strain at 23°C [73°F]—Original, no post cure						
100% Modulus, MPa [psi]	3.1 [455]	2.8 [400]	3.5 [505]	4.8 [695]	1.9 [280]	1.9 [280]
Tensile Strength, MPa [psi]	9.7 [1410]	10.2 [1480]	8.3 [1210]	9.3 [1345]	8.6 [1250]	10.0 [1455]
Elongation at Break, %	351	334	371	369	384	438
Hardness, durometer A, points	71	65	67	78	63	64
Stress/Strain at 23°C [73°F]—Original, post cure						
100% Modulus, MPa [psi]	4.5 [655]	3.5 [510]	5.8 [845]	9.8 [1420]	2.3 [340]	2.4 [355]
Tensile Strength, MPa [psi]	13.5 [1955]	13.7 [1990]	11.4 [1650]	16.1 [2340]	12.0 [1735]	13.8 [2000]
Elongation at Break, %	237	242	242	176	324	297
Hardness, durometer A, points	77	68	69	77	65	66
Stress/Strain at 23°C [73°F]—After aging 70 hr at 200°C [392°F]						
100% Modulus, MPa [psi]	4.6 [670]	3.7 [540]	5.8 [840]	10.0 [1445]	2.5 [360]	2.5 [360]
Tensile Strength, MPa [psi]	14.5 [2100]	12.7 [1840]	10.8 [1565]	16.1 [2340]	10.9 [1580]	13.5 [1955]
Elongation at Break, %	240	218	214	175	281	281
Hardness, durometer A, points	75	66	68	79	62	65
Stress/Strain at 23°C [73°F]—After aging 168 hr at 200°C [392°F]						
100% Modulus, MPa [psi]	4.5 [655]	3.6 [515]	5.6 [815]	11.0 [1590]	2.4 [345]	2.6 [375]
Tensile Strength, MPa [psi]	15.0 [2180]	12.8 [1850]	10.9 [1575]	16.4 [2375]	11.6 [1680]	13.1 [1905]
Elongation at Break, %	263	233	244	168	323	280
Hardness, durometer A, points	72	70	68	79	62	66
Stress/Strain at 23°C [73°F]—After aging 70 hr at 232°C [450°F]						
100% Modulus, MPa [psi]	4.9 [710]	3.6 [515]	5.3 [765]	10.0 [1455]	2.3 [340]	2.3 [340]
Tensile Strength, MPa [psi]	14.1 [2040]	13.4 [1940]	10.7 [1555]	16.0 [2320]	11.1 [1605]	14.2 [2055]
Elongation at Break, %	230	241	231	172	301	303
Hardness, durometer A, points	76	68	68	81	61	67
Compression Set, Method B, O-rings, %						
70 hr at 23°C [73°F]	18	11	12	15	12	17
70 hr at 200°C [392°F]	21	20	18	22	17	23
168 hr at 200°C [392°F]	29	30	25	32	23	29
70 hr at 232°C [450°F]	40	44	40	44	37	43

Test Procedures

Property Measured	Test Procedure
Compression Set	ASTM D395, Method B (25% deflection)
Compression Set, O-Rings	ASTM D1414
Hardness	ASTM D2240, durometer A
Mooney Scorch	ASTM D1646, using small rotor. Minimum viscosity and time to a 1-, 2-, 5-, and 10-unit rise are reported.
Mooney Viscosity	ASTM D1646, ten pass 121°C
ODR (vulcanization characteristics measured with an oscillating disk cure meter)	ASTM D2084
Property Change After Oven Heat-Aging	ASTM D573
Stress/Strain Properties 100% Modulus Tensile Strength Elongation at Break	ASTM D412, pulled at 8.5 mm/s (20 in/min)
Volume Change in Fluids	ASTM D471-79

Note: Test temperature is 24°C [75°F] except where specified otherwise.

Proprietary Materials

Sources of compounding ingredients used in developing the information in this bulletin are listed below. This is not to imply that comparable ingredients from other sources might not be equally usable.

Material	Composition	Supplier
Albaglos®	Calcium Carbonate (precipitated)	Pfizer, Inc. M.P.M. Division New York, NY 10017
Blanc Fixe	Barium Sulfate (precipitated)	Whittaker, Clark & Daniels (Distributor) South Plainfield, NJ 07080
Celite® 350	Diatomaceous Silica	Manville Corp. & Subsidiaries Denver, CO 80217
Nyad 400®	Calcium Metasilicate	Interpace Corporation Parsippany, NJ 07054
Ti-Pure® R960	Rutile Titanium Oxide	DuPont Company Wilmington, DE 19898

For further information please contact one of the offices below, or visit our website at www.dupontelastomers.com/viton

Global Headquarters—Wilmington, DE USA

Tel. +1-800-853-5515
+1-302-792-4000
Fax +1-302-792-4450

European Headquarters—Geneva

Tel. +41-22-717-4000
Fax +41-22-717-4001

South & Central America Headquarters—Brazil

Tel. +55-11-4166-8978
Fax +55-11-4166-8989

Asia Pacific Headquarters—Singapore

Tel. +65-6275-9383
Fax +65-6275-9395

Japan Headquarters—Tokyo

Tel. +81-3-6402-6300
Fax +81-3-6402-6301

The information set forth herein is furnished free of charge and is based on technical data that DuPont Performance Elastomers believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe on any patents. While the information presented here is accurate at the time of publication, specifications can change. Please check www.dupontelastomers.com for the most up-to-date information.

CAUTION: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, discuss with your DuPont Performance Elastomers Customer Service Representative, and read Medical Caution Statement H-69237.

DuPont™ is a trademark of DuPont and its affiliates.

Viton® is a registered trademark of DuPont Performance Elastomers.

Copyright © 2005 DuPont Performance Elastomers L.L.C. All rights reserved.